



ASSOCIATION CONNECTING
ELECTRONICS INDUSTRIES®

IPC-4412A

Specification for Finished Fabric Woven from "E" Glass for Printed Boards

Developed by the Woven Glass Reinforcement Task Group (3-12d) of the Strategic Components of Base Materials Subcommittee (3-12) of the Printed Board Base Materials Committee (3-10) of IPC

Supersedes:

IPC-4412 - June 2002
IPC-EG-140 with Amendments
1 & 2 - June 1997
IPC-EG-140 - March 1988

Users of this publication are encouraged to participate in the development of future revisions.

Contact:

IPC
3000 Lakeside Drive, Suite 309S
Bannockburn, Illinois
60015-1219
Tel 847 615.7100
Fax 847 615.7105

Table of Contents

1	SCOPE	1	3.2.3	Conversion from US System to SI	3
1.2	Purpose	1	3.3	Visual Requirements	3
1.3	Designation	1	3.4	Physical Requirements	3
2	APPLICABLE DOCUMENTS	1	3.4.1	Fabric Count	3
2.1	IPC	1	3.4.2	Weave Type	3
2.2	American Society for Testing and Materials (ASTM)	1	3.4.3	Fabric Thickness	3
2.3	International Standards	1	3.4.4	Fabric Weight	3
2.4	National Conference of Standards Laboratories (NCSL)	1	3.4.5	Fabric Length	3
3	REQUIREMENTS	1	3.4.6	Fabric Width	3
3.1	Terms and Definitions	1	3.4.7	Feather Length	3
3.1.1	AQL (Acceptable Quality Level)	1	3.4.8	Filament Diameter	4
3.1.2	Bias	1	3.4.9	Bare Glass Nominal Measurement	4
3.1.3	Bow	1	3.5	Chemical Requirements	4
3.1.4	Creases	1	3.5.1	Finish Level (Organic Content)	4
3.1.5	Defects	1	3.6	Workmanship	4
3.1.5.1	Major Defect	1	3.7	Laser Machinability Performance	4
3.1.5.2	Minor Defect	1	3.8	Alternate Fabric Styles and Weaves	4
3.1.5.3	Defect per Hundred Units	1	4	QUALITY ASSURANCE	4
3.1.6	E Glass (Electrical Grade Glass Fiber)	1	4.1	Statistical Process Control (SPC)	4
3.1.7	End Missing	2	4.2	Responsibility for Inspection	5
3.1.8	Feather Length	2	4.2.1	Test Equipment and Inspection Facilities	5
3.1.9	Fabric Finish	2	4.2.2	Preparation of Samples	5
3.1.10	Fish Eye	2	4.2.3	Standard Laboratory Conditions	5
3.1.11	Leno End Out	2	4.3	Inspection Requirements and Acceptability	5
3.1.12	Lot or Batch Size	2	4.3.1	Sample Size	5
3.1.13	Mark	2	4.3.2	Sampling Plans	5
3.1.13.1	Heavy Mark	2	4.3.3	Acceptable Quality Level (AQL)	5
3.1.13.2	Light Mark	2	4.4	Test Methods	6
3.1.14	Pick	2	4.4.1	Fabric Appearance	6
3.1.14.1	Broken Pick	2	4.4.2	Fabric Count	6
3.1.14.2	Mis-picks	2	4.4.3	Weave Type	6
3.1.15	Plain Weave	2	4.4.4	Fabric Thickness	6
3.1.16	Splits	2	4.4.5	Weight per Unit Area	6
3.1.17	Tears	2	4.4.6	Fabric Length	6
3.1.18	TEX System	2	4.4.7	Fabric Width	7
3.1.19	Waste	2	4.4.8	Finish Level (Organic Content)	7
3.1.20	Waviness	2	4.4.9	Bias or Bowed Filling	7
3.2	Yarn Nomenclature	2	5	PREPARATION FOR DELIVERY	7
3.2.1	US System	2	5.1	Preservation and Packaging	7
3.2.2	SI/Metric	2	5.2	Packing	7
			5.3	Marking	7

6	NOTES	7
6.1	Ordering Data	7
6.2	New Styles	7
Appendix I		8
Appendix II	Finished Fabric Glass Styles SI Units	10
Appendix II	Finished Fabric Glass Styles US System	12

Tables

Table 3-1	Classification of Defects	3
Table 3-2	Filament Diameter Designations	4
Table 3-3	Bare Glass Nominal Measurements	4
Table 4-1	Sample Size per Number of Rolls Shipped	5
Table 4-2	Sample Size per Yardage of Individual Roll Shipped and the Acceptable Quality Level	5
Table I-1	Cross Reference Between IPC-4412, Standards Called Out by IPC-4412, and ISO Documents	8
Table I-2	Cross Reference Between IPC-4412, ASTM and ISO Documents	9
Table II-1	Finished Fabric Glass Styles in SI Units	10
Table II-2	Finished Fabric Glass Styles for US System	12

Specification for Finished Fabric Woven from "E" Glass for Printed Boards

1 SCOPE

This specification covers finished fabrics woven from "E" glass electrical grade glass fiber yarns that are intended as a reinforcing material in laminated plastics for electrical and electronic use. All fabrics covered by this specification are plain weave.

1.2 Purpose This specification determines the nomenclature, definitions, general and chemical requirements for the glass, and physical requirements for finished woven glass fiber fabrics.

1.3 Designation Appendix II of this standard provides a style designator for each finished fabric glass style, with specifications on yarn, fabric count, thickness and weight in both SI and US system. Fabrics listed in Appendix II also categorize fabrics by their current availability status.

2 APPLICABLE DOCUMENTS

2.1 IPC¹

IPC-T-50 Terms and Definitions for Interconnecting and Packaging Electronic Circuits

IPC-9191 General Guidelines for Implementation of Statistical Process Control (SPC)

2.2 American Society for Testing and Materials (ASTM)²

ASTM-D578 Standard Specification for Glass Fiber Strands

ASTM-D1776 Standard Practice for Conditioning Testing Textiles

2.3 International Standards³

ISO 9001 Quality Management Systems - Requirements

2.4 National Conference of Standards Laboratories (NCSL)⁴

NCSL Z 540-1 General Requirements for Calibration Laboratories and Measuring and Test Equipment

3 REQUIREMENTS

3.1 Terms and Definitions The definition of terms shall be in accordance with IPC-T-50 and the following:

3.1.1 AQL (Acceptable Quality Level) Maximum number of defects per hundred units that can be considered satisfactory as a process average.

3.1.2 Bias Filling yarns are off-square to the warp ends.

3.1.3 Bow Filling yarns lie in an arc across the width of the fabric.

3.1.4 Creases A ridge in the fabric caused by a fold or wrinkle being placed under pressure.

3.1.5 Defects A substandard area in a fabric.

3.1.5.1 Major Defect A defect that is likely to result in failure, or to reduce materially the usability of the unit of product for its intended purpose.

3.1.5.2 Minor Defect A defect that is not likely to reduce materially the usability of the unit of product for its intended purpose.

3.1.5.3 Defect per Hundred Units

$$\frac{\text{Number of Defects}}{\text{Number of Units Inspected}} \times 100$$

3.1.6 E Glass (Electrical Grade Glass Fiber) E glass, which is to be used for PWB applications, is a continuous filament glass yarn with a chemical composition by weight that is within the following limits:

B ₂ O ₃	5% - 10%
CaO	16% - 25%
Al ₂ O ₃	12% - 16%
SiO ₂	52% - 56%
MgO	0% - 5%
Na ₂ O and K ₂ O	0% - 2%
TiO ₂	0% - 0.8%
Fe ₂ O ₃	0.05% - 0.4%
F ₂	0% - 1.0%

1. www.ipc.org

2. www.astm.org

3. www.iso.ch

4. www.ncsl-h9.org