



IPC-4412B

Specification for Finished Fabric Woven from “E” Glass for Printed Boards

Developed by the Woven Glass Reinforcement Task Group (3-12d) of
the Printed Board Base Materials Committee (3-10) of IPC

Supersedes:

IPC-4412A with Amendments
1, 2 & 3 - July 2011
IPC-4412A - January 2006
IPC-4412 - June 2002
IPC-EG-140 with Amendments
1 & 2 - June 1997
IPC-EG-140 - March 1988

Users of this publication are encouraged to participate in the
development of future revisions.

Contact:

IPC
3000 Lakeside Drive, Suite 309S
Bannockburn, Illinois
60015-1219
Tel 847 615.7100
Fax 847 615.7105

Table of Contents

1 SCOPE	1	3.1.21 Waste	3
1.2 Purpose	1	3.1.22 Waviness	3
1.3 Designation	1	3.2 Yarn Nomenclature	3
2 APPLICABLE DOCUMENTS	1	3.2.1 US System	3
2.1 IPC	1	3.2.2 SI/Metric	3
2.2 American Society for Testing and Materials (ASTM)	1	3.2.3 Conversion from US System to SI	4
2.3 International Standards	1	3.3 Visual Requirements	4
2.4 National Conference of Standards Laboratories (NCSL)	1	3.4 Physical Requirements	4
3 REQUIREMENTS	1	3.4.1 Fabric Count	4
3.1 Terms and Definitions	1	3.4.2 Weave Type	4
3.1.1 AQL (Acceptable Quality Level)	1	3.4.3 Fabric Thickness	4
3.1.2 Bias	1	3.4.4 Fabric Weight	4
3.1.3 Bow	1	3.4.5 Fabric Length	4
3.1.4 Creases	1	3.4.6 Fabric Width	4
3.1.5 Defects	1	3.4.7 Feather Length	5
3.1.5.1 Major Defect	2	3.4.8 Filament Diameter	5
3.1.5.2 Minor Defect	2	3.4.9 Bare Glass Nominal Measurement	5
3.1.5.3 Defect per Hundred Units	2	3.5 Chemical Requirements	6
3.1.6 E Glass (Electrical Grade Glass Fiber)	2	3.5.1 Finish Level (Organic Content)	6
3.1.6.1 Permittivity (Dielectric Constant) for Bulk Form E Glass	2	3.6 Workmanship	6
3.1.7 End Missing	2	3.7 Laser Machinability Performance	6
3.1.8 Feather Length	2	3.8 Alternate Fabric Styles and Weaves	6
3.1.9 Fabric Finish	2	4 QUALITY ASSURANCE	6
3.1.10 Fish Eye	2	4.1 Statistical Process Control (SPC)	6
3.1.11 Hollow Filament	2	4.2 Responsibility for Inspection	6
3.1.12 Leno End Out	2	4.2.1 Test Equipment and Inspection Facilities	6
3.1.13 Lot or Batch Size	2	4.2.2 Preparation of Samples	6
3.1.14 Mark	2	4.2.3 Standard Laboratory Conditions	7
3.1.14.1 Heavy Mark	2	4.3 Inspection Requirements and Acceptability	7
3.1.14.2 Light Mark	2	4.3.1 Sample Size	7
3.1.15 Pick	3	4.3.2 Sampling Plans	7
3.1.15.1 Broken Pick	3	4.3.3 Acceptable Quality Level (AQL)	7
3.1.15.2 Mis-picks	3	4.4 Test Methods	8
3.1.16 Plain Weave	3	4.4.1 Fabric Appearance	8
3.1.17 Splits	3	4.4.2 Fabric Count	8
3.1.18 Spread Glass Fabric	3	4.4.3 Weave Type	8
3.1.19 Tears	3	4.4.4 Fabric Thickness	8
3.1.20 TEX System	3	4.4.5 Weight per Unit Area	8
		4.4.6 Fabric Length	9
		4.4.7 Fabric Width	9
		4.4.8 Finish Level (Organic Content)	9
		4.4.9 Bias or Bowed Filling	9

5	PREPARATION FOR DELIVERY	9
5.1	Preservation and Packaging	9
5.2	Packing	9
5.3	Marking	9
6	NOTES	10
6.1	Ordering Data	10
6.2	New Styles	10
Appendix I	11
Appendix II	Finished Fabric Glass Styles	
	SI Units	13
Appendix II	Finished Fabric Glass Styles	
	US System	16

Tables

Table 3-1	Classification of Defects	4
Table 3-2	Filament Diameter Designations	5
Table 3-3	Bare Glass Nominal Measurements	5
Table 4-1	Sample Size per Number of Rolls Shipped	7
Table 4-2	Sample Size per Yardage of Individual Roll Shipped and the Acceptable Quality Level	7
Table AI-1	Cross Reference Between IPC-4412, Standards Called Out by IPC-4412, and ISO Documents	11
Table AI-2	Cross Reference Between IPC-4412, ASTM and ISO Documents	12
Table AII-1	Finished Fabric Glass Styles in SI Units	13
Table AII-2	Finished Fabric Glass Styles for US System ...	16

Specification for Finished Fabric Woven from “E” Glass for Printed Boards

1 SCOPE

This specification covers finished fabrics woven from “E” glass electrical grade glass fiber yarns that are intended as a reinforcing material in laminated plastics for electrical and electronic use. All fabrics covered by this specification are plain weave.

1.2 Purpose This specification determines the nomenclature, definitions, general and chemical requirements for the glass, and physical requirements for finished woven glass fiber fabrics.

1.3 Designation Appendix II of this standard provides a style designator for each finished fabric glass style, with specifications on yarn, fabric count, thickness and weight in both SI and US system. Fabrics listed in Appendix II also categorize fabrics by their current availability status.

2 APPLICABLE DOCUMENTS

2.1 IPC¹

IPC-T-50 Terms and Definitions for Interconnecting and Packaging Electronic Circuits

IPC-9191 General Guidelines for Implementation of Statistical Process Control (SPC)

2.2 American Society for Testing and Materials (ASTM)²

ASTM D578 Standard Specification for Glass Fiber Strands

ASTM D579 Standard Specification for Greige Woven Glass Fabrics

ASTM D1776 Standard Practice for Conditioning Testing Textiles

2.3 International Standards³

ISO 9001 Quality Management Systems - Requirements

2.4 National Conference of Standards Laboratories (NCSL)⁴

NCSL Z 540-1 General Requirements for Calibration Laboratories and Measuring and Test Equipment

3 REQUIREMENTS

3.1 Terms and Definitions The definition of terms shall be in accordance with IPC-T-50 and 3.1.1 through 3.1.21.

3.1.1 AQL (Acceptable Quality Level) Maximum number of defects per hundred units that can be considered satisfactory as a process average.

3.1.2 Bias Filling yarns are off-square to the warp ends.

3.1.3 Bow Filling yarns lie in an arc across the width of the fabric.

3.1.4 Creases A ridge in the fabric caused by a fold or wrinkle being placed under pressure.

3.1.5 Defects A substandard area in a fabric.

1. www.ipc.org

2. www.astm.org

3. www.iso.ch

4. www.ncsl-h9.org