



IPC J-STD-004B

# Requirements for Soldering Fluxes

A standard developed by the Flux Specifications Task Group (5-24a)  
of the Assembly and Joining Processes Committee (5-20) of IPC

***Supersedes:***

J-STD-004A - January 2004

J-STD-004 - January 1995

Amendment 1 - April 1996

Users of this publication are encouraged to participate in the  
development of future revisions.

Contact:

**IPC**

3000 Lakeside Drive, Suite 309S

Bannockburn, Illinois 60015-1249

Tel 847 615.7100

Fax 847 615.7105

# Table of Contents

<b>1</b>	<b>SCOPE AND DESIGNATION</b>	1	3.4.2.1	Flux Solids (Nonvolatile) Determination	6
1.1	Scope	1	3.4.2.2	Acid Value Determination	6
1.2	Purpose	1	3.4.2.3	Specific Gravity Determination	6
1.3	Designation	1	3.4.2.4	Viscosity of Paste (Tacky) Flux	7
1.4	Interpretation “ <b>Shall</b> ”	1	3.4.2.5	Visual	7
<b>2</b>	<b>APPLICABLE DOCUMENTS</b>	2	3.5	Optional Testing	7
2.1	IPC	2	3.5.1	Optional Qualitative Halide Tests	7
2.2	Joint Industry Standards	2	3.5.1.1	Chlorides and Bromides by Silver Chromate Method	7
2.3	American Society for Testing and Materials (ASTM)	2	3.5.1.2	Fluorides By Spot Test	7
2.4	British Standards	2	3.5.2	Optional SIR Tests	7
2.5	International Organization for Standards	2	3.5.2.1	Reporting Values for Optional SIR Test Methods	7
2.6	National Conference of Standards Laboratories (NCSL)	2	3.5.3	Optional Fungus Resistance Test	7
2.7	Telcordia Technologies	2	3.6	Quality Conformance Testing	7
2.8	International Electrotechnical Commission (IEC)	2	3.6.1	Acid Value Determination	7
2.9	Registration, Evaluation, Authorization and Restriction of Chemicals (REACH)	3	3.6.2	Specific Gravity Determination	7
<b>3</b>	<b>GENERAL REQUIREMENTS</b>	3	3.6.3	Viscosity of Paste (Tacky) Flux	7
3.1	Conflict	3	3.6.4	Visual	7
3.2	Terms and Definitions and Acronyms	3	3.7	Performance Testing	7
3.2.1	ECM	3	3.7.1	Wetting Balance Test	7
3.2.2	SIR	3	3.7.2	Spread Test - Liquid Flux	7
3.2.3	Supplier	3	<b>4</b>	<b>QUALIFICATION AND QUALITY ASSURANCE PROVISIONS</b>	7
3.3	Flux Qualification	3	4.1	Responsibility for Inspection	7
3.3.1	Classification	3	4.1.1	Responsibility for Compliance	7
3.3.1.1	Flux Composition	3	4.1.1.1	Quality Assurance Program	7
3.3.1.2	Flux Type	4	4.1.2	Test Equipment and Inspection Facilities	7
3.3.1.2.1	Flux Activity	4	4.1.3	Inspection Conditions	8
3.3.1.2.2	Halide Content	4	4.2	Types of Inspections	8
3.3.2	Characterization	4	4.3	Qualification Inspection	8
3.4	Qualification Testing	4	4.3.1	Sample Size	8
3.4.1	Classification Testing	4	4.3.2	Inspection Routine	8
3.4.1.1	Copper Mirror Test	4	4.3.3	Requalification	9
3.4.1.2	Corrosion Test	4	4.3.3.1	Formula Variations Constituting Material Change	9
3.4.1.3	Quantitative Halide Content Tests	6	4.3.3.2	Manufacturing Site Change	9
3.4.1.4	SIR Test	6	4.4	Quality Conformance Inspection	9
3.4.1.4.1	Reporting SIR Test Results	6	4.4.1	Sampling Plan	9
3.4.1.5	Test Resistance to ECM	6	4.4.2	Rejected Lots	9
3.4.1.5.1	Reporting ECM Test Results	6	4.5	Performance Inspection	9
3.4.2	Characterization Testing	6	<b>Appendix A</b>	<b>Example Qualification Test Report</b>	10
			<b>Appendix B</b>	<b>Notes</b>	10

**Figures**

Figure 3-1	Flux Corrosivity by Copper Mirror Test .....	5
Figure 3-2	Example of No Corrosion .....	5
Figure 3-3	Example of Minor Corrosion .....	5
Figure 3-4	Example of Major Corrosion .....	6
Figure B-1	Typical Wetting Balance Curve .....	12

**Tables**

Table 1-1	Flux Identification System .....	1
Table 3-1	Preparation of Flux Forms for Testing .....	3
Table 3-2	Test Requirements for Flux Classification .....	4
Table 4-1	Qualification, Quality Conformance and Performance Testing for Flux .....	8
Table B-1	Spread Area Requirements .....	13

# Requirements for Soldering Fluxes

## 1 SCOPE AND DESIGNATION

**1.1 Scope** This standard prescribes general requirements for the classification and characterization of fluxes for high quality solder interconnections. This standard may be used for quality control and procurement purposes.

**1.2 Purpose** The purpose of this standard is to classify and characterize tin/lead and lead-free soldering flux materials for use in electronic metallurgical interconnections for printed circuit board assembly. Soldering flux materials include the following: liquid flux, paste flux, solder paste, solder cream, and flux-coated and flux-cored solder wires and preforms. It is not the intent of this standard to exclude any acceptable flux or soldering material; however, these materials must produce the desired electrical and metallurgical interconnection.

The requirements for fluxes are defined in general terms for standard classification. Appendix B has additional information that will help users understand some of the requirements of this standard. In practice, where more stringent requirements are necessary or other manufacturing processes are used, the user **shall** define these as additional requirements.

**1.3 Designation** For ordering purposes and designation by other specifications, the following flux identification system **shall** be used (see Table 1-1).

**1.4 Interpretation “Shall”** The imperative form of the verb is used throughout this standard whenever a requirement is intended to express a provision that is mandatory. Deviation from a “**shall**” requirement may be considered if sufficient information is supplied to justify the exception.

Table 1-1 Flux Identification System

Flux Composition	Flux/Flux Residue Activity Levels	% Halide <sup>1</sup> (by weight)	Flux Type <sup>2</sup>	Flux Designator
Rosin (RO)	Low	<0.05%	L0	ROLO
		<0.5%	L1	ROL1
	Moderate	<0.05%	M0	ROM0
		0.5-2.0%	M1	ROM1
	High	<0.05%	H0	ROH0
		>2.0%	H1	ROH1
Resin (RE)	Low	<0.05%	L0	RELO
		<0.5%	L1	REL1
	Moderate	<0.05%	M0	REM0
		0.5-2.0%	M1	REM1
	High	<0.05%	H0	REH0
		>2.0%	H1	REH1
Organic (OR)	Low	<0.05%	L0	ORLO
		<0.5%	L1	ORL1
	Moderate	<0.05%	M0	ORM0
		0.5-2.0%	M1	ORM1
	High	<0.05%	H0	ORH0
		>2.0%	H1	ORH1
Inorganic (IN)	Low	<0.05%	L0	INL0
		<0.5%	L1	INL1
	Moderate	<0.05%	M0	INM0
		0.5-2.0%	M1	INM1
	High	<0.05%	H0	INH0
		>2.0%	H1	INH1

1. Halide measuring <0.05% by weight in flux solids and may be known as halide-free. This method determines the amount of ionic halide present (see Appendix B-10).

2. The 0 and 1 indicate the absence or presence of halides, respectively. See paragraph 3.3.1.2.2 for flux type nomenclature.