



IPC-4101E-WAM1

Specification for Base Materials for Rigid and Multilayer Printed Boards

Developed by the Laminate/Prepreg Materials Subcommittee (3-11) of
the Printed Board Base Materials Committee (3-10) of IPC

Supersedes:

IPC-4101E - March 2017
IPC-4101D-WAM1 - July 2015
IPC-4101D - April 2014
IPC-4101C - August 2009
IPC-4101B with
Amendments 1 & 2 - April 2007
IPC-4101B with
Amendment 1 - February 2007
IPC-4101B - June 2006
IPC-4101A with
Amendment 1 - June 2002
IPC-4101A - December 2001
IPC-4101 - December 1997
IPC-L-108
IPC-L-109
IPC-L-112
IPC-L-115
IPC-AM-361

Users of this standard are encouraged to participate in the
development of future revisions.

Contact:

IPC

Table of Contents

1	SCOPE	1	3.5	Verification of Manufacturer's Quality System	11
1.1	Classification	1	3.6	Conflict	11
1.1.1	Specification Sheet Description	1	3.7	Materials	11
1.1.2	Nominal Laminate Thickness	1	3.7.1	Metal Cladding	11
1.1.3	Metal Cladding Type and Nominal Weight/ Thickness	2	3.7.2	Reinforcement Fabric	11
1.1.4	Thickness Tolerance (Laminate)	2	3.7.3	Resin Systems	11
1.1.5	Surface Quality Class	2	3.8	General Requirements	11
1.1.6	Reinforcement Style	2	3.8.1	Fabricated Sheets and Panels	11
1.1.7	Prepreg Parameters	2	3.8.2	Inspection Lot	12
1.1.8	Color	4	3.8.3	Visual Properties	12
1.2	Dimensions and Tolerances	4	3.8.4	Dimensional	14
1.2.1	Metric and Imperial Measurements	4	3.9	Physical Requirements	15
2	APPLICABLE DOCUMENTS	4	3.9.1	Physical Requirements of Laminate Materials	15
2.1	IPC	4	3.9.2	Physical Requirements of Prepreg Materials	17
2.2	National Conference of Standards Laboratories (NCSL)	6	3.10	Chemical Requirements	18
2.3	International Standards	6	3.10.1	Chemical Requirements of Laminate Materials	18
2.4	Underwriters Laboratories (UL)	6	3.10.2	Chemical Requirements of Prepreg Materials	20
2.5	European Union	6	3.11	Electrical Requirements	20
2.6	ASTM International	6	3.11.1	Electrical Requirements of Laminate Materials	20
3	REQUIREMENTS	6	3.11.2	Electrical Requirements of Prepreg Materials	20
3.1	Terms and Definitions	6	3.12	Environmental Requirements	20
3.1.1	Qualification Assessment	6	3.12.1	Environmental Requirements of Laminate Materials	20
3.1.2	Quality Conformance Testing	6	3.12.2	Environmental Requirements of Prepreg Materials	21
3.1.3	Supplier's Quality System	6	3.13	Substitutability	21
3.1.4	Process Control Testing	6	3.13.1	Permissible Substitutions of Specification Sheet Materials	21
3.1.5	Self Declaration	6	3.13.2	Substitutability of Classes of Pits and Dents	21
3.1.6	Quality Assessment Data	7	3.13.3	Substitutability of Classes of Thickness Tolerance	21
3.1.7	Sample Qualification	7	3.13.4	Remarking of Substituted Laminates	21
3.1.8	Production Data	7	3.14	Marking	21
3.1.9	Customer Test Data	7	3.14.1	Marking Laminate Materials	21
3.1.10	Internal Assessment	7	3.14.2	Marking Prepreg Materials	22
3.1.11	Individual Customer Audit	7	3.14.3	Marking of Shipping Containers	22
3.1.12	Independent Third Party Assessment	7	3.15	Workmanship	22
3.1.13	Epoxy, Multifunctional	7	3.16	Material Safety	22
3.1.14	Epoxy, Difunctional	7	3.17	Prepreg Shelf Life	22
3.1.15	AABUS	7			
3.2	Specification Sheets	7			
3.3	Manufacturer Quality Profile	7			
3.4	Qualification Testing	7			
3.4.1	Qualification Testing of Laminate	11			
3.4.2	Qualification Testing of Prepreg	11			

4 QUALITY ASSURANCE PROVISIONS 22

4.1 Quality System 22

4.2 Responsibility for Inspection 22

4.2.1 Test Equipment and Inspection Facilities 23

4.3 Qualification Testing 23

4.3.1 Samples 23

4.3.2 Frequency 23

4.3.3 Laminator Qualification Profile 23

4.3.4 Changes in Composition 23

4.3.5 Qualification Data Retention 23

4.4 Quality Conformance Inspection 23

4.4.1 Frequency 23

4.4.2 Acceptance Criteria 24

4.4.3 Rejected Lots 24

4.4.4 Conformance Data Retention 24

4.4.5 Certificate of Conformance 24

4.5 Statistical Process Control (SPC) 24

5 PREPARATION FOR DELIVERY 24

5.1 Packaging Materials 24

5.2 Authorized Distributors 24

6 NOTES 25

6.1 Ordering Information 25

6.1.1 Ordering Data for Laminate Materials 25

6.1.2 Ordering Data for Prepreg Materials 25

6.2 New Materials 25

7 KEYWORDS 26

7.1 Keyword Search Terms (Electronic/Soft Copy Searches) 26

7.2 Segmented Keyword Search Terms and All Specification Sheets that Use the Specific Key Words for Searching 26

7.3 Keyword Search Terms for All Specification Sheets 26

APPENDIX A (IPC-4101 supplemental inspection requirements if required in purchase order or master drawing) 162

Figures

Figure 3-1 Thickness Measurements for Laminates 15

Tables

Table 1-1 Metal Cladding Types 2

Table 1-2 Copper Foil Weight and Thickness 3

Table 3-1 Reference Information and Test Frequency of Laminate 8

Table 3-2 Reference Information and Test Frequency of Prepreg 10

Table 3-3 Point Value for Longest Dimensions of Indentation 12

Table 3-4 Surface Quality Classification 13

Table 3-5 Permissible Variation in Length and Width of Laminates 14

Table 3-6 Permissible Variation in Length and Width of Prepregs 14

Table 3-7 Thickness and Tolerances for Laminates 16

Table 3-8 Permissible Bow and Twist for Laminates, % .. 16

Table 3-9 Flammability Requirements 19

Table 3-10 Permissible Material Substitutions 21

Table 4-1 Quality Conformance Plan for Monthly, Quarterly and Annual Tests – Laminate 23

Table 4-2 Quality Conformance Plan for Monthly, Quarterly and Annual Tests – Prepreg 23

Specification for Base Materials for Rigid and Multilayer Printed Boards

1 SCOPE

This specification covers the requirements for base materials, herein referred to as laminate or prepreg, to be used primarily for rigid or multilayer printed boards for electrical and electronic circuits.

1.1 Classification The system shown below identifies clad and unclad laminate or prepreg base materials. The specification sheets serve as a cross-reference connecting the outlined callout system in this document to previously used systems.

Example for laminate base materials where this specification is referenced:

- L Material Designator (see 1.1.1)
- 25 Specification Sheet Number (see 1.1.1)
- 1500 Nominal Laminate Thickness (see 1.1.2)
- C1/C1 Metal Cladding Type and Nominal Weight/Thickness (see 1.1.3)
- A Thickness Tolerance Class (see 1.1.4)
- A Surface Quality Class (see 1.1.5)

Example for prepreg base materials where this specification is referenced:

- P Material Designator (see 1.1.1)
- 25 Specification Sheet Number (see 1.1.1)
- E7628 Reinforcement Style (see 1.1.6)
- TW Resin Content Method (see 1.1.7)
- RE Flow Parameter Method (see 1.1.7)
- VC Optional Prepreg Method (see 1.1.7)

1.1.1 Specification Sheet Description At the end of this document is a series of specification sheets. Each specification sheet outlines requirements for both laminate and prepreg for each product grade. The specification sheets are organized by a specific reinforcement type, resin system, and/or construction and are provided with a specification sheet number for ordering purposes. For convenience, the laminate and prepreg requirements for materials of the like composition are on the same specification sheet. Material Designator “L” indicates laminate material and Material Designator “P” indicates prepreg material as shown in designation examples in 1.1. When certifying to multiple specification sheets, the strongest performance requirements **shall** apply.

The headings for each specification sheet include reference definitions for the material, which cover the reinforcements, resin systems, flame retardants, and fillers used, as well as its other known identifications and glass transition temperature, T_g . The specific line items within the specification sheets are the requirements that material **shall** meet in order to be certified to this specification.

Specification sheets have no cancellation date. When no revision of IPC-4101 is called out, the latest revision of IPC-4101 **shall** apply. If previous revisions are used, then the specification sheet and revision **shall** be called out.

1.1.2 Nominal Laminate Thickness The nominal thickness is identified by four digits. For all substrates covered by this document, thicknesses may be specified or measured either over the cladding or over the dielectric (see 1.1.4 and 3.8.4.2). For metric specification, the first digit represents whole millimeters, the second represents tenths of millimeters, etc. For orders requiring Imperial units, the four digits indicate the thickness in ten-thousandths of an inch. In the example shown in 1.1, 1500 designates a laminate with thickness of 1.5 mm [0.0591 in], which would be specified as 0591 when using Imperial units.